



# Annalyce Gold Data Sheet

## Wet Slip Resistance

Finish	Value	Classification
Exfoliated	59 (+2)	P5

## Analysis

## Results

Mean Dried Compressive Strength (MPa)	127 (+1.5)
Mean Soaked Compressive Strength (MPa)	125 (+1.5)
Mean Mass Resistance to Salt Attack (%)	0.01 (+0.03)
Mean Bulk Specific Gravity (kg/m <sup>3</sup> )	2,617 (+2)
Mean Absorption by Volume (%)	0.77 (+0.07)
Mean Absorption by Weight (%)	0.30 (+0.03)
Mean Index of Abrasion Resistance (Ha)	102.9 (+12.6)
Mean Dried Modulus of Rupture (MPa)	11.3 (+0.1)
Mean Soaked Modulus of Rupture (MPa)	11.8 (+0.1)



OUTDOOR FINISH  
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]