



Anstone Data Sheet


Wet Slip Resistance

Finish	Value	Classification
Sandblasted	65 (+2)	P5
Bush Hammered	59 (+2)	P5
Honed	32 (+2)	P2

Analysis

Results

Mean Dried Compressive Strength (MPa)	114 (+1.4)
Mean Soaked Compressive Strength (MPa)	84 (+1.0)
Mean Mass Resistance to Salt Attack (%)	0.45 (+0.03)
Mean Bulk Specific Gravity (kg/m ³)	2,716 (+2)
Mean Absorption by Volume (%)	2.81 (+0.08)
Mean Absorption by Weight (%)	1.04 (+0.03)
Mean Index of Abrasion Resistance (Ha)	21.6 (+0.6)
Mean Dried Modulus of Rupture (MPa)	14.3 (+0.2)
Mean Soaked Modulus of Rupture (MPa)	15.9 (+0.2)
Mean Luminous Reflectance (Yd/Yw) - Not Sealed	Yd: 21 Yw: 8



OUTDOOR FINISH
SANDBLASTED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]