



# Ash Black Data Sheet

## Wet Slip Resistance

Finish	Value	Classification
Exfoliated	63	P5
Bush Hammered	47	P5

## Analysis

## Results

Flexural Strength Dried (MPa)	18.6 (+0.4)
Flexural Strength Soaked (MPa)	16.9 (+0.3)
Mean Bulk Specific Gravity (kg/m <sup>3</sup> )	2,914 (+2)
Mean Absorption by Volume (%)	0.3 (+0.08)
Mean Absorption by Weight (%)	0.1 (+0.03)
Mean Compressive Strength Dried (Mpa)	211 (193-237)
Mean Compressive Strength Soaked (Mpa)	174 (129-208)



OUTDOOR FINISH  
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]