



Austral Juperana Data Sheet


Wet Slip Resistance

| Finish | Value | Classification |
|------------|-------|----------------|
| Exfoliated | V | P5 |

Analysis

Results

| | |
|--------------------------------------------|-------|
| Mean Absorption by Volume (%) | 0.30% |
| Compressive Strength / Average Dry | 176 |
| Compressive Strength / Average Soaked | 162 |
| Flexural Strength (MPa) / Average Dry | 10.9 |
| Flexural Strength (MPa) / Average Soaked | 9.9 |
| Mean Luminous Reflectance / Average Soaked | 14.3 |
| Mean Luminous Reflectance / Average Dry | 30.21 |
| Mean Index of Abrasion Resistance (Ha) | 3 |



OUTDOOR FINISH
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]