



# Basalt Black Data Sheet

## Wet Slip Resistance

Finish	Value	Classification
Exfoliated	68 (+2)	P5

## Analysis

## Results

Mean Dried Compressive Strength (MPa)	272
Mean Soaked Compressive Strength (MPa)	229
Mean Mass Resistance to Salt Attack (%)	.23
Mean Bulk Specific Gravity (kg/m <sup>3</sup> )	2,906 (+2)
Mean Absorption by Weight (%)	0.81
Mean Absorption by Volume (%)	0.74
Mean Index of Abrasion Resistance (Ha)	52
Mean Dried Modulus of Rupture (MPa)	23.2
Mean Soaked Modulus of Rupture (MPa)	27.5



OUTDOOR FINISH  
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]