



Hazy White Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	61 (+2)	P5
Bush Hammered	71 (+2)	P5
Sandblasted	63 (+2)	P5

Analysis

Results

Mean Dried Compressive Strength (MPa)	154 (+1.9)
Mean Soaked Compressive Strength (MPa)	145 (+1.7)
Mean Mass Resistance to Salt Attack (%)	0.02 (+0.03)
Mean Bulk Specific Gravity (kg/m ³)	2,600 (+2)
Mean Absorption by Volume (%)	0.88 (+0.08)
Mean Absorption by Weight (%)	0.34 (+0.03)
Mean Index of Abrasion Resistance (Ha)	87 (+9.0)
Mean Dried Modulus of Rupture (MPa)	11.2 (+0.1)
Mean Soaked Modulus of Rupture (MPa)	10.2 (+0.1)



OUTDOOR FINISH
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]