



Honey Jasper Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	64 (+2)	P5
Bush Hammered	75 (+2)	P5

Analysis

Results

Mean Dried Compressive Strength (MPa)	153 (+1.8)
Mean Soaked Compressive Strength (MPa)	126 (+1.5)
Mean Mass Resistance to Salt Attack (%)	0.06 (+0.02)
Mean Dried Luminous Reflectance (Y) - Sandblasted	45.5 (+2.9)
Mean Wet Luminous Reflectance (Y) - Sandblasted	26.2 (+2)
Mean Bulk Specific Gravity (kg/m ³)	2,586 (+2)
Mean Absorption by Volume (%)	1.11 (+0.08)
Mean Absorption by Weight (%)	0.43 (+0.03)
Mean Index of Abrasion Resistance (Ha)	98.1 (+11.6)
Mean Dried Modulus of Rupture (MPa)	11.6 (+0.1)
Mean Soak Modulus of Rupture (MPa)	10.8 (+0.1)
Crystalline Silica Minerals	36.7



OUTDOOR FINISH
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]