



Mosaic Red Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	61	P5

Analysis

Results

Mean Soaked Modulus of Rupture (MPa)	8.9 (+0.1)
Mean Dried Modulus of Rupture (MPa)	8.1 (+0.1)



[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]