



# Natural Bluestone Data Sheet

## Wet Slip Resistance

Finish	Value	Classification
Sandblasted	67 (+2)	P5
Bush Hammered	71 (+2)	P5
Scratched	67 (+2)	P5

## Analysis

## Results

Mean Dried Compressive Strength (MPa)	143 (+1.7)
Mean Soaked Compressive Strength (MPa)	126 (+1.5)
Mean Mass Resistance to Salt Attack (%)	0.34 (+0.03)
Mean Bulk Specific Gravity (kg/m <sup>3</sup> )	2,700 (+2)
Mean Absorption by Volume (%)	3.57 (+0.07)
Mean Absorption by Weight (%)	1.32 (+0.03)
Mean Index of Abrasion Resistance (Ha)	44.7 (+2.4)
Mean Dried Modulus of Rupture (MPa)	16.3 (+0.2)
Mean Soak Modulus of Rupture (MPa)	14.5 (+0.2)



OUTDOOR FINISH  
SANDBLASTED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]