



# Raven Black Data Sheet

## Wet Slip Resistance

Finish	Value	Classification
Exfoliated	57	P5
Bushhammered	79	P5

## Analysis

## Results

Mean Dried Compressive Strength (MPa)	234 (+2.8)
Mean Soaked Compressive Strength (MPa)	208 (+2.5)
Mean Mass Resistance to Salt Attack (%)	0.07 (+0.03)
Mean Bulk Specific Gravity (kg/m <sup>3</sup> )	2,980 (+2)
Mean Absorption by Volume (%)	0.17 (+0.08)
Mean Absorption by Weight (%)	0.06 (+0.03)
Mean Index of Abrasion Resistance (Ha)	101.1 (+10.9)
Mean Dried Modulus of Rupture (MPa)	19.0 (+0.2)
Mean Soak Modulus of Rupture (MPa)	17.8 (+0.2)
Crystalline Silica Minerals	0.7



OUTDOOR FINISH  
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]