



Sesame Green Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	63 (+2)	P5
Bush Hammered	66 (+2)	P5

Analysis

Results

Mean Dried Compressive Strength (MPa)	196 (+2.4)
Mean Soaked Compressive Strength (MPa)	190 (+2.3)
Mean Mass Resistance to Salt Attack (%)	0.09 (+0.03)
Mean Bulk Specific Gravity (kg/m ³)	2,871 (+2)
Mean Absorption by Volume (%)	0.26 (+0.07)
Mean Absorption by Weight (%)	0.09 (+0.03)
Mean Index of Abrasion Resistance (Ha)	64.0 (+4.5)
Mean Dried Modulus of Rupture (MPa)	34.9 (+0.4)
Mean Soak Modulus of Rupture (MPa)	39.0 (+0.5)



OUTDOOR FINISH
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]