



Austral Verde Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	V	P5

Analysis

Results

Mean Absorption by Volume (%)	0.04%
Compressive Strength / Average Dry	214
Compressive Strength / Average Soaked	202
Flexural Strength (MPa) / Average Dry	15.4
Flexural Strength (MPa) / Average Soaked	15.9
Mean Bulk Density (kg/m ³)	2643
Mean Index of Abrasion Resistance (Ha)	146



OUTDOOR FINISH
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]