



Wisteria Dark Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	58 (+2)	P5
Bush Hammered	65 (+2)	P5

Analysis

Results

Mean Dried Compressive Strength (MPa)	151 (+1.8)
Mean Soaked Compressive Strength (MPa)	154 (+1.8)
Mean Mass Resistance to Salt Attack (%)	0.03 (+0.03)
Mean Bulk Specific Gravity (kg/m ³)	2,644 (+2)
Mean Absorption by Volume (%)	0.61 (+0.06)
Mean Absorption by Weight (%)	0.23 (+0.03)
Mean Index of Abrasion Resistance (Ha)	96 (+10.8)
Mean Dried Modulus of Rupture (MPa)	8.7 (+0.1)
Mean Soak Modulus of Rupture (MPa)	8.7 (+0.1)



OUTDOOR FINISH
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]