



# Desert Rose Data Sheet

## Wet Slip Resistance

| Finish     | Value | Classification |
|------------|-------|----------------|
| Exfoliated | 65    | P5             |

## Analysis

## Results

|                                          |       |
|------------------------------------------|-------|
| Mean Dired Compressive Strength (MPa)    | 145   |
| Mean Soaked Compressive Strength (MPa)   | 122   |
| Water Absorption (% by Weight)           | 0.19% |
| Dried Flexural Strength (MPa) / Average  | 11.5  |
| Soaked Flexural Strength (MPa) / Average | 11.4  |
| Bulk Density (Kg/m <sup>3</sup> )        | 2930  |
| Abrasion Resistance (Ha)                 | 125   |



OUTDOOR FINISH  
EXFOLIATED

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]