



Ash Black Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	63	P5
Bush Hammered	47	P5

Analysis

Results

Bulk Specific Gravity (Kg/m ³)	2,914 (±2)
Crystalline Silica (%)	11.4
Flexural Strength (MPa)	
Average Dried	18.6 (±0.4)
Average Soaked	16.9 (±0.3)
Luminous Reflectance - Exfoliated Finish (Unsealed)	
Average Dried (Yd)	13.12
Average Soaked (Yw)	10.51
Unconfined Compressive Strength (MPa)	
Average Dried	211 (±2.5)
Average Soaked	174 (±2.1)
Water Absorption (%)	
Average by Volume	0.3 (±0.08)
Average by Weight	0.1 (±0.03)



FINISH > EXFOLIATED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.