



Austral Coffee Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	61	P5

Analysis

Results

Flexural Strength (MPa)	
Average Dried	9.9
Average Soaked	10.9
Luminous Reflectance (Unsealed)	
Average Dried (Yd)	30.21
Average Soaked (Yw)	14.43
Unconfined Compressive Strength (MPa)	
Average Dried	176
Average Soaked	162
Water Absorption (%)	
Average by Volume	0.30



FINISH > EXFOLIATED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.