



Austral Verde Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	60 (± 2)	P5

Analysis

Results

Abrasion Resistance (Ha)	146
Bulk Density (Kg/m ³)	2,643
Coefficient of Lineal Thermal Expansion	7.9×10^{-6}
Crystalline Silica (%)	18
Flexural Strength (MPa)	
Average Dried	15.4 (± 0.3)
Average Soaked	15.9 (± 0.3)
Unconfined Compressive Strength (MPa)	
Average Dried	214 (± 2.5)
Average Soaked	202 (± 2.4)
Water Absorption (%)	
Average by Weight	0.04



FINISH > EXFOLIATED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.