



Basalt Black Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	68 (± 2)	P5

Analysis

Results

Abrasion Resistance (Ha)	55.2 (± 3.3)
Bulk Specific Gravity (Kg/m ³)	2,906 (± 2)
Crystalline Silica (%)	0
Modulus of Rupture (MPa)	
Average Dried	30.6 (± 0.4)
Average Soaked	27.1 (± 0.3)
Resistance to Salt Attack (%)	0.23 (± 0.03)
Unconfined Compressive Strength (MPa)	
Average Dried	272 (± 3.3)
Average Soaked	229 (± 2.7)
Water Absorption (%)	
Average by Volume	0.74 (± 0.08)
Average by Weight	0.25 (± 0.03)



FINISH > EXFOLIATED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.