



Desert Rose Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	65	P5

Analysis

Results

Abrasion Resistance (Ha)	125
Bulk Density (Kg/m ³)	2,930
Flexural Strength (MPa)	
Average Dried	11.5
Average Soaked	11.4
Unconfined Compressive Strength (MPa)	
Average Dried	145
Average Soaked	122
Water Absorption (%)	
Average by Weight	0.19



FINISH > EXFOLIATED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.