



Grigio Travertine Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Sandblasted	65 (± 2)	P5

Analysis

Results

Crystalline Silica (%)	0
Modulus of Rupture (MPa)	
Average Dried	18.4 (± 0.3)
Average Soaked	13.7 (± 0.2)
Water Absorption (%)	
Average by Weight	0.5



FINISH > SANDBLASTED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.