



# Hazy White Data Sheet

## Wet Slip Resistance

Finish	Value	Classification
Exfoliated	61 ( $\pm 2$ )	P5
Bush Hammered	71 ( $\pm 2$ )	P5
Sandblasted	63 ( $\pm 2$ )	P5



FINISH &gt; EXFOLIATED

## Analysis

## Results

Abrasion Resistance (Ha)	87 ( $\pm 9$ )
Bulk Specific Gravity (Kg/m <sup>3</sup> )	2,600 ( $\pm 2$ )
Crystalline Silica (%)	40
Luminous Reflectance - Exfoliated Finish	
Average Dried (Yd)	52.7
Average Soaked (Yw)	53.1
Modulus of Rupture (MPa)	
Average Dried	11.2 ( $\pm 0.1$ )
Average Soaked	10.2 ( $\pm 0.1$ )
Resistance to Salt Attack (%)	0.02 ( $\pm 0.03$ )
Unconfined Compressive Strength (MPa)	
Average Dried	154 ( $\pm 1.9$ )
Average Soaked	145 ( $\pm 1.7$ )
Water Absorption (%)	
Average by Volume	0.88 ( $\pm 0.08$ )
Average by Weight	0.34 ( $\pm 0.03$ )

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.