



# Honey Jasper Data Sheet

## Wet Slip Resistance

Finish	Value	Classification
Exfoliated	64	P5
Bush Hammered	75	P5
Sandblasted	67	P5
Honed	36	P3



FINISH &gt; EXFOLIATED

## Analysis

## Results

Abrasion Resistance (Ha)	98.1 (±11.6)
Bulk Specific Gravity (Kg/m <sup>3</sup> )	2,586 (±2)
Crystalline Silica (%)	36.7
Luminous Reflectance - Bush Hammered Finish	
Average Dried (Yd)	45.6
Average Soaked (Yw)	42.2
Luminous Reflectance - Exfoliated Finish	
Average Dried (Yd)	37.6
Average Soaked (Yw)	35.0
Luminous Reflectance - Sandblasted Finish	
Average Dried (Yd)	45.5
Average Soaked (Yw)	26.2
Modulus of Rupture (MPa)	
Average Dried	11.6 (±0.1)
Average Soaked	10.8 (±0.1)
Resistance to Salt Attack (%)	0.06 (±0.03)
Unconfined Compressive Strength (MPa)	
Average Dried	153 (±1.8)
Average Soaked	126 (±1.5)
Water Absorption (%)	
Average by Volume	1.11 (±0.08)
Average by Weight	0.43 (±0.03)

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.