



Italia Porphyry Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Natural Split	66 (±2)	P5

Analysis

Results

Crystalline Silica (%)	38.7
Luminous Reflectance - Brown and Grey Tones	
Average Dried (Yd)	15.45
Average Soaked (Yw)	13.35
Luminous Reflectance - Darker Brown and Grey Tones	
Average Dried (Yd)	8.95
Average Soaked (Yw)	8.02
Luminous Reflectance - Yellow, Gold and Brown Tones	
Average Dried (Yd)	11.84
Average Soaked (Yw)	10.31
Modulus of Rupture (MPa)	
Average Dried	19.1 (±0.2)
Average Soaked	18.4 (±0.2)



FINISH > NATURAL SPLIT

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.