




Jarraah Red Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Bush Hammered	69 (± 2)	P5
Exfoliated	52 (± 2)	P5



FINISH > EXFOLIATED

Analysis

Results

Abrasion Resistance (Ha)	104.7 (± 13.4)
Bulk Specific Gravity (Kg/m ³)	2,596 (± 2)
Crystalline Silica (%)	16
Modulus of Rupture (MPa)	
Average Dried	29.1 (± 0.3)
Average Soaked	26.8 (± 0.3)
Resistance to Salt Attack (%)	0.16 (± 0.03)
Unconfined Compressive Strength (MPa)	
Average Dried	202 (± 2.4)
Average Soaked	128 (± 1.5)
Water Absorption (%)	
By Weight	0.53 (± 0.03)
By Volume	1.37 (± 0.07)

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.