



Komo Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Natural Split	52	P4

Analysis

Results

Abrasion Resistance (Ha)	136.3 (± 7.6)
Bulk Specific Gravity (Kg/m ³)	2,628 (± 2)
Crystalline Silica (%)	59.7
Modulus of Rupture (MPa)	
Average Dried	23.6 (± 0.3)
Average Soaked	16.0 (± 0.2)
Resistance to Salt Attack (%)	<0.1
Unconfined Compressive Strength (MPa)	
Average Dried	160 (± 1.9)
Average Soaked	120 (± 1.4)
Water Absorption (%)	
Average by Volume	0.87 (± 0.09)
Average by Weight	0.33 (± 0.03)



FINISH > NATURAL SPLIT

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.