



# Mosaic Red Data Sheet

## Wet Slip Resistance

Finish	Value	Classification
Exfoliated	61 ( $\pm 2$ )	P5

## Analysis

## Results

Crystalline Silica (%)	30
Modulus of Rupture (MPa)	
Average Dried	8.9 ( $\pm 0.1$ )
Average Soaked	8.1 ( $\pm 0.1$ )



FINISH &gt; EXFOLIATED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.