



Natural Bluestone Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Sandblasted	67 (± 2)	P5
Bush Hammered	71 (± 2)	P5
Scratched	67 (± 2)	P5
Honed	34 (± 2)	P2



FINISH > SANDBLASTED

Analysis

Results

Abrasion Resistance (Ha)	44.7 (± 2.4)
Bulk Specific Gravity (Kg/m ³)	2,700 (± 2)
Modulus of Rupture (MPa)	
Average Dried	16.3 (± 0.2)
Average Soaked	14.5 (± 0.2)
Resistance to Salt Attack (%)	0.34 (± 0.03)
Unconfined Compressive Strength (MPa)	
Average Dried	143 (± 1.7)
Average Soaked	126 (± 1.5)
Water Absorption (%)	
Average by Volume	3.57 (± 0.07)
Average by Weight	1.32 (± 0.03)

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.