



Raven Black Data Sheet


Wet Slip Resistance

Finish	Value	Classification
Exfoliated	57	P5
Bush Hammered	79	P5

Analysis

Results

Abrasion Resistance (Ha)	101.1 (± 10.9)
Bulk Specific Gravity (Kg/m ³)	2,980 (± 2)
Crystalline Silica (%)	0.7
Luminous Reflectance - Exfoliated Finish	
Average Dried (Yd)	12.2
Average Soaked (Yw)	5.3
Modulus of Rupture (MPa)	
Average Dried	19.0 (± 0.2)
Average Soaked	17.8 (± 0.2)
Resistance to Salt Attack (%)	0.07 (± 0.03)
Unconfined Compressive Strength (MPa)	
Average Dried	234 (± 2.8)
Average Soaked	208 (± 2.5)
Water Absorption (%)	
Average by Volume	0.17 (± 0.0)
Average by Weight	0.06 (± 0.03)



FINISH > EXFOLIATED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.