



Sesame Green Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	63	P5
Bush Hammered	66	P5

Analysis

Results

Abrasion Resistance (Ha)	64 (±4.5)
Bulk Specific Gravity (Kg/m ³)	2,871 (±2)
Modulus of Rupture (MPa)	
Average Dried	34.9 (±0.4)
Average Soaked	39.0 (±0.5)
Resistance to Salt Attack (%)	0.09 (±0.03)
Unconfined Compressive Strength (MPa)	
Average Dried	196 (±2.4)
Average Soaked	190 (±2.3)
Water Absorption (%)	
Average by Volume	0.26 (±0.07)
Average by Weight	0.09 (±0.03)



FINISH > EXFOLIATED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.