



Sesame Grey Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	61	P5
Bush Hammered	65	P5
Leather	59	P5
Sandblasted	54	P4
Scratched	59	P5



FINISH > EXFOLIATED

Analysis

Results

Abrasion Resistance (Ha)	91.9 (± 9.5)
Bulk Specific Gravity (Kg/m ³)	2,799 (± 2)
Crystalline Silica (%)	19
Luminous Reflectance	
Average Dried (Yd)	23
Average Soaked (Yw)	9.1
Modulus of Rupture (MPa)	
Average Dried	25.8 (± 0.3)
Average Soaked	26.0 (± 0.3)
Resistance to Salt Attack (%)	0.03 ($\pm 0.03\%$)
Unconfined Compressive Strength (MPa)	
Average Dried	177 (± 2.1)
Average Soaked	177 (± 2.1)
Water Absorption (%)	
Average by Volume	0.28% (± 0.08)
Average by Weight	0.10% (± 0.03)

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.