



Shadow Grey Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Sandblasted & Lightly Tumbled	54 (± 2)	P4

Analysis

Results

Abrasion Resistance (Ha)	43.3 (± 0.8)
Breaking Load (kN)	
Average Dried	3.5 (± 0.10)
Crystalline Silica (%)	0
Modulus of Rupture (MPa)	
Average Dried	8.1
Resistance to Salt Attack (Method B)	
Mean Weight Loss (g)	
After 15 Cycles	0.22
After 23 Cycles	0.85
Grade for Flags & Pavers	G
Water Absorption (%)	
Average by Weight	0.6



FINISH > SANDBLASTED & LIGHTLY TUMBLED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.