



# Silver Black Data Sheet

## Wet Slip Resistance

Finish	Value	Classification
Exfoliated	59 ( $\pm 2$ )	P5
Bush Hammered	67 ( $\pm 2$ )	P5

## Analysis

## Results

Abrasion Resistance (Ha)	106.1 ( $\pm 12.5$ )
Bulk Specific Gravity (Kg/m <sup>3</sup> )	2,844 ( $\pm 2$ )
Crystalline Silica (%)	7
Luminous Reflectance - Exfoliated Finish	
Average Dried (Yd)	13.41
Average Soaked (Yw)	11.99
Modulus of Rupture (MPa)	
Average Dried	19.9 ( $\pm 0.2$ )
Average Soaked	17.3 ( $\pm 0.2$ )
Resistance to Salt Attack (%)	0.06 ( $\pm 0.03$ )
Unconfined Compressive Strength (MPa)	
Average Dried	139 ( $\pm 1.7$ )
Average Soaked	119 ( $\pm 1.4$ )
Water Absorption (%)	
Average by Volume	0.29 ( $\pm 0.08$ )
Average by Weight	0.10 ( $\pm 0.03$ )



FINISH &gt; EXFOLIATED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.