



Wisteria Dark Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	58 (± 2)	P5
Bush Hammered	65 (± 2)	P5

Analysis

Results

Abrasion Resistance (Ha)	95.6 (± 10.8)
Crystalline Silica (%)	7
Bulk Specific Gravity (Kg/m ³)	2,644 (± 2)
Coefficient of Linear Thermal Expansion	10.9x10 ⁻⁶
Modulus of Rupture (MPa)	
Average Dried	8.7 (± 0.1)
Average Soaked	8.7 (± 0.1)
Resistance to Salt Attack (%)	0.03 (± 0.03)
Unconfined Compressive Strength (MPa)	
Average Dried	151 (± 1.8)
Average Soaked	154 (± 1.8)
Water Absorption (%)	
Average by Volume	0.61 (± 0.06)
Average by Weight	0.23 (± 0.03)



FINISH > EXFOLIATED

Disclaimer: Due to the inherent variability of natural stone, the results are indicative.