



Italia Porphyry Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Natural Split	66 (+2)	P5

Analysis

Results

Mean Dried Compressive Strength (MPa)	19.1 (+0.2)
Mean Soaked Modulus of Rupture	18.4 (+0.2)
Luminous Reflective Value / Average Dry (Yellow, Gold and Brown tones)	11.84
Luminous Reflective Value / Average Wet (Yellow, Gold and Brown tones)	10.31
Luminous Reflective Value / Average Dry (Darker Brown and Grey tones Exfoliated)	8.95
Luminous Reflective Value / Average Wet (Darker Brown and Grey tones Exfoliated)	8.02
Luminous Reflective Value / Average Dry (Brown and Grey tones Exfoliated)	15.45
Luminous Reflective Value / Average Wet (Brown and Grey tones Exfoliated)	13.35
Crystalline Silica Minerals	38.7



OUTDOOR FINISH
NATURAL SPLIT

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]