



Sesame Grey Data Sheet

Wet Slip Resistance

Finish	Value	Classification
Exfoliated	55	P5
Bush Hammered	57	P5
Sandblasted	54	P4
Scratched	55	P5



OUTDOOR FINISH
EXFOLIATED

Analysis

Results

Mean Dried Compressive Strength (MPa)	177 (+2.1)
Mean Soaked Compressive Strength (MPa)	177 (+2.1)
Mean Mass Resistance to Salt Attack (%)	0.03 (+0.03)
Mean Bulk Specific Gravity (kg/m ³)	2,799 (+2)
Mean Absorption by Volume (%)	0.28 (+0.08)
Mean Absorption by Weight (%)	0.10 (+0.03)
Mean Index of Abrasion Resistance (Ha)	92 (+9.5)
Mean Dried Modulus of Rupture (MPa)	25.8 (+0.3)
Mean Soak Modulus of Rupture (MPa)	26.0 (+0.3)
Mean Luminous Reflectance (Yd/Yw) Exfoliated	Yd: 25.5 Yw: 7.6
Mean Luminous Reflectance (Yd/Yw) Bush Hammered	Yd: 31.4 Yw: 10.4
Crystalline Silica Minerals	19.0

[Disclaimer — Due to the inherent variability of natural stone, the results are indicative.]